

## STARFLEX 3050

Starflex 3050 is a superior performance aramid/synthetic fiber sheet sealing material bound with a high quality SBR.

### Service

Suitable for use in applications involving hot and cold water, saturated steam, and inert gases.

TEMPERATURE & PRESSURE	
Recommended Temperature	370 °C (825 °F)
Maximum Recommended Pressure	14 MPa (140 bar; 2030 psi)
These temperature and pressure guides cannot necessarily be used simultaneously and may not apply at all thickness.	
TYPICAL PHYSICAL PROPERTIES	
Thickness	1.5mm
Density	1.52g/cc
ASTM Compressibility	7% to 17%
ASTM Recovery	63%
ASTM Tensile Strength	20MPa
AVAILABILITY	
Sheet size	1.5m x 1.5m
Thickness range	0.4 mm to 3.0 mm

**Note:**

- a. For designing, variables will change with different thickness. Please contact Starflex for designing information.
- b. Recommended Surface Finish- 125rms to 500rms. Please refer to manufacturer.

---

**Head Office:** 15/B, Vinod Apartments, Krantiveer Vasant Rao Naik X Lane, Gowalia Tank. Mumbai – 400036 INDIA  
**Tel.:** 91 - 22 - 2389 0904 / 05 **Fax:** 91 - 22 - 2389 0907 **Email:** starflex@starflex.net  
**visit us at:** www.starflex.net

**Disclaimer:** The datasheet relates to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the company in relation to same. The acquisition of additional data may necessitate revision to parts, or all, of this data sheet, and such information will be supplied as it becomes available.

The information given and, in particular, any parameters, should be used for guidance purposes only. The company does not give any warranty that the product will be suitable for the use intended by the customer.